

龙牌



















# 阳离子染料

Dragonacrylic Dyes



寧波保稅區洪大化工實業有限公司  
NINGBO FREE TRADE ZONE HONGDA CHEMICAL INDUSTRIAL CO., LTD

龙牌阳离子染料 DRAGONACRYLIC		染色深度 Dyeing depth owf %	染料索引 C. I. Basic No.	配伍指数 K Value	饱和因数 F Value	色牢度 (1/1) Fastness		
染料名称 Name of Dyes	色样 Color Sample (晴纶) (Polyacrylonitrile)					耐光(氙灯) Light (Xenon)	耐洗 Washing 60°C	耐摩擦(干湿) (W/D) Rubbing
艳黄 X - 10GFF 300% Fl. Yellow X - 10GFF		0.5	Y   40	3.5	0.5	3	4	5 5
艳黄 X - 7GL 500% Brill. Yellow 7GL		0.38	Y   24	1.5	0.52	6	4-5	5 5
黄 X - 5GL 400% Yellow X - 5GL		0.25	Y   51	3.0	1.0	6	4-5	4-5 4-5
黄 7GLL 200% Yellow 7GLL		1.1	Y   21	2.5	0.29	4-5	4-5	5 4-5
黄 X - 8GL 250% Yellow X - 8GL		0.8	Y   13	3.5	0.75	4-5	4-5	5 4-5
黄 3GLH 200% Yellow 3GLH		0.5	Y   11	3.0	0.28	6-7	5	5 4
黄 M - RL 200% Yellow M - RL		0.4	Y   49	5	0.52	7-8	5	5 4-5
黄 GRL 200% Yellow GRL		0.5	Y   29	2.0	0.17	6-7	4-5	4-5 4-5
黄 3RL 200% Yellow 3RL		0.6	Y   67	3.0	0.6	6-7	5	5 5
黄 2RL 200% Yellow 2RL		0.4	Y   19	2	0.6	6-7	5	4-5 4-5
金黄 X - GL 250% Golden Yellow X - GL		0.44	Y   28	3	0.61	6-7	4-5	4-5 4-5
橙 G 400% Orange G		0.55	O   21	1.5	0.26	5	4-5	5 5
艳红 5GN 250% Brill. Red 5GN		0.5	R   14	3	0.5	4	4-5	4-5 4
桃红 FF 120% Pink FF		1.0	R   12	2	-	2	3-4	4 4
桃红 FG 250% Pink FG		0.6	R   13	4	0.46	4	4-5	5 5
红 2GL 250% Red 2GL		0.57	R   29	2	0.23	7	4-5	4-5 4-5
红 X - GRL 250% Red X - GRL		0.6	R   46	2.5	0.56	6-7	4-5	4-5 4
红 M - RL 200% Red M - RL		0.28	R   51	3.0	1.05	6-7	4-5	5 4-5

龙牌阳离子染料 DRAGONACRYLIC		染色深度 Dyeing depth owf %	染料索引 C. I. Basic No.	配伍指数 K Value	饱和因数 F Value	色牢度 (1/1) Fastness		
染料名称 Name of Dyes	色样 Color Sample (晴纶) (Polyacrylonitrile)					耐光(氙灯) Light (Xenon)	耐洗 Washing 60°C	耐摩擦(干湿) Rubbing (D, W)
红 GTLN 120% Red GTLN		1.3	R   18:1	3.5	0.38	6-7	5	4-5 4-5
红 GTL 200% Red GTL		0.8	R   18	2.5	0.72	5-6	4-5	4-5 4-5
桃红 B 300% Pink B		1.0	R   27	2.0	0.21	4	5	5 5
红 B 250% Red B		0.8	R   15	3.5	0.36	4-5	5	5 5
红 3R 300% Red 3R		0.3	V   16	1.5	0.5	4	4-5	4-5 5
红 X-6B 100% Red X-6B		0.35	V   7	3.0	0.26	4	4-5	4-5 4
紫 5BLH 200% Violet 5BLH		0.47	V   28	3.0	0.49	5	4-5	4-5 4
紫 3BL 250% Violet 3BL		0.48	B   53	1.5	0.31	5	3-4	4-5 4
蓝 M-RL 250% Blue M-RL		0.68	-	4.0	0.67	6-7	4-5	4-5 4-5
蓝 FRL 500% Blue FRL		0.55	B   162	3.0	0.14	6-7	4-5	4-5 4-5
艳蓝 RL 500% Brill. Blue RL		0.15	B   54	1.5	0.67	5-6	4-5	4-5 4-5
蓝 GSL 250% Blue GSL		0.3	B   54*	1.5	0.21	6-7	4	4-5 4-5
蓝 X-GRL 300% Blue X-GRL		0.35	B   41	3.0	0.4	6	4	4-5 4-5
蓝 X-BL 250% Blue X-BL		0.36	B   159	3.0	0.43	7	5	5 4-5
翠蓝 X-GB 250% Turq. Blue X-GB		0.53	B   3	3.5	0.31	4	4	4-5 4-5
藏青 X-BRL 250% Navy Blue X-BRL		0.6	-	3.0	0.58	5-6	4-5	4 3
深蓝 RB 300% Dark Blue RB		0.6	-	3.0	0.3	4-5	4	4-5 3-4
深棕 X-3RL 250% Dark Brown X-3RL		1.5	-	3.0	0.51	5-6	3-4	4-5 4-5

龙牌阳离子染料 DRAGONACRYLIC		染色深度 Dyeing depth owf %	染料索引 C. I. Basic No.	配伍指数 K Value	饱和因数 F Value	色牢度 (1/1) Fastness		
染料名称 Name of Dyes	色样 Color Sample (晴纶) (Polyacrylonitrile)					耐光(氙灯) Light (Xenon)	耐洗 Washing 60°C	耐摩擦(干湿) Rubbing (D, W)
黑 X - RL 100% Black X - RL		3.0	-	3.0	0.55	5-6	4-5	4-5 4
黑 X - 2RL 100% Black X - 2RL		3.0	-	3.0	0.35	6	4	4-5 4
黑 O 300% Black O		3.0	-	3.0	1.0	5	4-5	4-5 4-5
黄 SD - 10GFF 100% Yellow SD - 10GFF		2.0	Y   40	3.5	0.5	3	4	5 5
黄 SD - 7GL 100% Yellow SD - 7GL		2.0	Y   24	1.5	0.52	6	4-5	5 5
黄 SD - 5GL 100% Yellow SD - 5GL		2.0	Y   51	3.0	1.0	6	4-5	4-5 4-5
黄 SD - GRL 100% Yellow SD - GRL		2.0	Y   29	2	2	6-7	4-5	4-5 4-5
黄 SD - 3RL 120% Yellow SD - 3RL		2.0	Y   67	3.0	0.6	6-7	5	5 5
黄 SD - 2RL 100% Yellow SD - 2RL		2.0	Y   19	2	0.6	6-7	5	4-5 4-5
金黄 SD - GL 120% Golden Yellow SD - GL		2.0	Y   28	3	0.61	6-7	4-5	4-5 4-5
红 SD - 5GN 100% Red SD - 5GN		2.2	R   14	3	0.5	4	4-5	4-5 4
桃红 SD - FG 100% Pink SD - FG		2.2	R   13	4	0.46	4	4-5	5 5
红 SD - 2GL 120% Red SD - 2GL		2.0	R   29	1.5	0.52	7	4-5	4-5 4-5
红 SD - GRL 100% Red SD - GRL		2.0	R   46	2.5	0.56	6-7	4-5	4-5 4
蓝 SD - GSL 100% Blue SD - GSL		2.0	B   54	1.5	0.67	6-7	4	4-5 4-5
蓝 SD - GRL 100% Blue SD - GRL		2.0	B   41	3	0.4	6	4	4-5 4-5
蓝 SD - BL 120% Blue SD - BL		2.0	B   159	3	0.43	7	5	5 4-5
翠蓝 SD - GB 120% Turq. Blue SD - GB		3.0	B   3	3.5	0.15	4	4	4-5 4-5