

【类 型】 PU 低游离新国标固化剂 (HDX-*L 系列)

【Type】 Chinese GB Standard Low Free-TDI PU Hardener (HDX-*L series)

【产品特性】 色泽浅、游离 TDI 单体含量低、符合最新国标要求、相溶性优异、干速快、耐化学品性好、贮存稳定。

【Characteristics】 Light color, Low free-TDI, Eco-friendly, Meet the latest national standard, Super solubility, Fast drying, Excellent chemical resistance, Stability.

【应用范围】 1. PU 环保装修漆

2. 家具面漆

【Applications】 1. Green Decoration PU Paint

2. Furniture top coat

【规 格 (Specification)】

产品规格(specification) 产品指标(Index)	HDX-30L	HDX-35L	HDX-40L	HDX-45L	HDX-50L
外观(Appearance)	水白至微黄透明粘稠液体 (Colorless to pale yellow transparent viscous liquid)				
(Fe-Co) 色数(Color)	≤ 1				
%NCO	4.5 ± 0.5	5.3 ± 0.5	6.0 ± 0.5	6.8 ± 0.5	7.5 ± 0.5
%游离 TDI(%Free TDI)	≤ 0.6	≤ 0.7	≤ 0.8	≤ 0.9	≤ 1.0
%固含量(%Solid content)	30 ± 1	35 ± 1	40 ± 1	45 ± 1	50 ± 1
(25°C/ T-4/s) 粘度 (Viscosity)	10~12	10~14	11~16	12~19	14~25
(二甲苯) 溶忍度 (Solubility)	≥ 1.2	≥ 1.2	≥ 1.2	≥ 1.2	≥ 1.2
备注：以上为本公司常规产品，另可按客户要求，特别定制。 Remark: Above are regular product, we can also customized according to your requirement.					

【溶剂稀释性】

与酯类、酮类、醚酯类溶剂相溶性好，芳香族溶剂有限可溶，脂肪族溶剂不可溶。使用前请先试验在溶剂中的稳定性及溶剂对漆膜的影响。

【Solubility】

Soluble in esters, ketones, and ether-ester solvent. Limited in aromatic solvent, insoluble in aliphatic solvent. Please test the stability of the curing agent in the solvent and the effect to the paint film before using.

【包装规格】 铁油桶装，净重 200Kg/桶。固含量低于 28% 以下净重 190Kg/桶。

【Delivery form】 Net weight: 200KG/drum or 190Kg/ drum if the solid content less than 28%.