

**【类型】** PU 无苯低游离固化剂（HDX-\*M 系列）

**【Type】** Low Free-TDI Benzene-free PU Hardener Series（HDX-\*M series）

**【产品特性】** 色泽浅、粘度低、游离 TDI 单体含量低、不含苯及其同系物、具突出环保效应、相溶性佳、硬度高、耐化学品性好、贮存稳定。

**【Characteristics】** Light color, low viscosity, Low free-TDI, Benzene series free solvent, Green decoration, super solubility, high hardness, excellent chemical resistance, Stability.

**【应用范围】** 1. PU 环保装修漆 2. PU 家具漆

**【Applications】** 1. Green Decoration PU Paint 2. PU Furniture paint

**【规格 (Specification)】**

产品规格(specification) 产品指标(Index)	HDX-30M	HDX-35M	HDX-40M	HDX-45M	HDX-50M
外观(Appearance)	水白至微黄透明粘稠液体 (Colorless to pale yellow transparent liquid)				
(Fe-Co) 色数(Color)	≤1				
%NCO	4.8±0.5	5.6±0.5	6.4±0.5	7.2±0.5	8.0±0.5
%游离 TDI(%Free TDI)	≤1.2	≤1.4	≤1.6	≤1.8	≤2.0
%固含量(%Solid content)	30±1	35±1	40±1	45±1	50±1
(25°C/ T-4/s) 粘度 (Viscosity)	10~12	11~14	12~16	13~19	14~25
(二甲苯) 溶忍度 (Solubility)	≥1.5	≥1.5	≥1.5	≥1.5	≥1.5
备注：以上为本公司常规产品，另可按客户要求，特别定制。 Remark: Above are regular product, we can also customized according to your requirement.					

**【溶剂稀释性】**

与酯类、酮类、醚酯类溶剂相溶性好，芳香族溶剂有限可溶，脂肪族溶剂不可溶。使用前请先试验在溶剂中的稳定性及溶剂对漆膜的影响。

**【Solubility】**

Soluble in esters, ketones, and ether-ester solvent. Limited in aromatic solvent, insoluble in aliphatic solvent. Please test the stability of the curing agent in the solvent and the effect to the paint film before using.

**【包装规格】** 铁油桶装，净重 200Kg/桶。固含量低于 28%以下净重 190Kg/桶。

**【Delivery form】** Net weight: 200KG/drum, 190KG/ drum for the solid content < 28%.