

**【类型】** PU 面漆专用型固化剂 (DX-\*A 系列)

**【Type】** Top Coat Specialized PU Hardener (DX-\*A series)

**【产品特性】** 色泽浅、粘度低、硬度高、丰满度优异、具良好流平性和透明度、耐黄变性好, 贮存稳定。

**【Characteristics】** Light color, Low viscosity, High hardness, Good fullness, Excellent leveling property, Good transparence, Good anti-yellowing, Stability.

**【应用范围】** 1. PU 家具面漆固化剂, 适用于高级 PU 涂料制造 2. 接着架桥剂

**【Applications】** 1. PU furniture top coat, especially for high-grade PU paints 2. Cross linking agent

**【规格 (Specification)】**

产品规格(specification) 产品指标(Index)	DX-30A	DX-35A	DX-40A	DX-45A	DX-50A
外观(Appearance)	水白至微黄透明粘稠液体 (Colorless to pale yellow transparent liquid)				
(Fe-Co) 色数(Color)	≤1				
%NCO	5.4±0.5	6.3±0.5	7.2±0.5	8.1±0.5	9.0±0.5
%固含量(%Solid content)	30±1	35±1	40±1	45±1	50±1
(25°C/ T-4/s) 粘度 (Viscosity)	10~12	10~14	11~15	12~18	14~20
(二甲苯) 溶忍度 (Solubility)	≥1.2	≥1.0	≥1.0	≥1.0	≥1.0
备注: 以上为本公司常规产品, 另可按客户要求, 特别定制。 Remark: Above are regular product, we can also customized according to your requirement.					

**【溶剂稀释性】**

与酯类、酮类、醚酯类溶剂相容性好, 芳香族溶剂有限可溶, 脂肪族溶剂不可溶。使用前请先试验在溶剂中的稳定性及溶剂对漆膜的影响。

**【Solubility】**

Soluble in esters, ketones, and ether-ester solvent. Limited in aromatic solvent, insoluble in aliphatic solvent. Please test the stability of the curing agent in the solvent and the effect to the paint film before using.

**【包装规格】** 铁油桶装, 净重 200Kg/桶。固含量低于 28%以下净重 190Kg/桶。

**【Delivery form】** Net weight: 200KG/drum or 190Kg/ drum if the solid content less than 28%.