



# Specification

## FB208 Silk gold rainbow

Edition: YZ2019-01 TDS

Assays		Values		Method
<b>Content</b>	<b>CAS-NO.</b>	<b>CI-NO.</b>		
Mica	12001-26-2	77019	50~59 wt%	YUNZHU
TiO <sub>2</sub>	13463-67-7	77891	41~49 wt%	YUNZHU
SnO <sub>2</sub>	18282-10-5	77861	≤1 wt%	YUNZHU
<b>Visual evaluation</b>				
Color			pass	YUNZHU
Luster			pass	YUNZHU
Density		2.7 ~ 3.3	g /cm <sup>3</sup>	ISO 787-10
Bulk density		19 ~ 25	g /100ml	DIN 53466
Particle size	80 % within the range	10~40μm	pass	Laser diffraction
PH – value	10 % aqueous slurry	5~9		ISO 787-9
Loss on drying	105 °C	≤0.5	wt %	ISO 787-2
Oil absorption		50 ~ 90	g oil/100g powder	ISO 787-5
<b>Conductance</b>		≤100	μs/cm	ISO 787-14
<b>Heavy metals</b>				
		Pb	≤ 30 ppm	YUNZHU
		As	≤ 5 ppm	YUNZHU
		Hg	≤ 1 ppm	YUNZHU
		Cd	≤ 5 ppm	YUNZHU

### **Shanghai Yunzhu Pigment Technology Co.,Ltd.**

No.27 Lane 111, Shunda Road, Nanxiang Town, Jiading Area, Shanghai, China.

Tel: 0086-21-56377935 / 56373532

Fax: 0086-21-66102842

Home Page: [www.chinayunzhu.com](http://www.chinayunzhu.com)

E-mail: [shyz@chinayunzhu.com](mailto:shyz@chinayunzhu.com)