

Reduction with Titanium Dioxide(1:2)

原色

用钛白粉 (1:2)冲淡色


U02



U03



U04




U06



U08



U08MX



The actual colour is based on the samples we sent you. This colour shade is only for your reference.
本色卡仅作客户参考之用, 确切的颜色将以我公司发出的样品为准。



Compatible and suitable for all kinds of polymers

Maintains dimensional stability :non-warping/non-shrinking

Non-Toxic

Excellent heat resistance(up to 350 ° C, 10 min)

主要特征和性能：

适用于各种聚合物

保持尺寸稳定，无翘曲变形

无毒

极佳耐热性（350 ° C，10分钟内不变色）

无迁移，卓越的耐候性

| Grade 型号 | Water soluble salts 水溶物 % | Sieve residue on 0.0045mm 筛余物 % | PH 值 | | Free Sulfur 硫含量 % | Moisture 105°C 挥发物 | Oil absorption 约g/100g 吸油量 | | Tinting strength 着色力 | |
|-------------|------------------------------|---------------------------------------|--------------|--------------|----------------------|--------------------------|----------------------------------|--------------|-------------------------|--------------|
| | max.% 最大% | max.% 最大% | min.% 最小% | max.% 最大% | max.% 最大% | max.% 最大% | min.% 最小% | max.% 最大% | min.% 最小% | max.% 最大% |
| U02 | 1.5 | 0.5 | 7.5 | 10 | 0.3 | 1.0 | 25.0 | 45.0 | 95 | 105 |
| U03 | 1.5 | 0.1 | 7.5 | 10 | 0.15 | 1.0 | 25.0 | 45.0 | 95 | 105 |
| U04 | 1.5 | 0.1 | 7.5 | 10 | 0.10 | 1.0 | 25.0 | 45.0 | 95 | 105 |
| U06 | 1.5 | 0.1 | 7.5 | 10 | 0.15 | 1.0 | 25.0 | 45.0 | 95 | 105 |
| U08 | 1.5 | 0.1 | 7.5 | 10 | 0.15 | 1.0 | 25.0 | 45.0 | 95 | 105 |
| U08max | 1.5 | 0.1 | 7.5 | 10 | 0.15 | 1.0 | 25.0 | 45.0 | 95 | 105 |

This product meets ISO788:1974(Ultramarine pigments for paints), it could be widely used in range of plastics, rubber, paints, coating, soap, detergent powder, artist pigments, inks and papers.

本品符合ISO788:1974标准（油漆用群青颜料），广泛用于塑料，橡胶，油漆，涂料，肥皂，洗衣粉，画家用颜料，墨水和纸张等行业。

Package and Storage:

Packed in color kraft bag with 25kg net weight, Keep storing in dry and ventilated places, avoided from moisture, acid & alkali, Period of validity for one year. Your special package also could be supplied.

包装和储存：

牛皮纸复合袋，净重25公斤。存于干燥通风处，避免接触酸碱物，未拆包装有效期为一年。

可以按客户要求协议包装或形式包装。

