BG-T6066、BG-T6068锤纹助剂 Hammer additives

组份/Component: 特殊改性聚硅氧烷溶液

Special modified polysiloxane solution

性能及用途/Properties and uses:

品 名 Name	外 观 Appearance	密度 Density (25℃)g/cm³	不挥发份% Non-volatile solvents%	风点℃ Flash point℃	溶剂 Solvent
BG-T6066	无色透明液体 Colorless liquid	0.91	10	> 25	二甲苯 xylene
BG-T6068	无色透明液体 Colorless liquid	0.92	10	> 25	二甲苯 xylene

BG-T6066

可以用较小的添加量, 使涂料获得美丽的立体锤纹效果。漆膜外观花纹醒目、立体感强。

According a small added, can get the beautiful stereoscopic paint hammer effect. Paint film's appearance is eyecatching patterns and strong stereoscopic sense.

BG-T6068

为特殊的表面纹理调节剂,可以使铝粉漆花纹均匀、致密精美、立体感突出。鉴于本品分子结构稳定,在贮存过程中

花纹不会发生较大变化。
As a unique surface texture regulator can make aluminum paint pattern uniform, dense fine, stereoscopic prominent. In view of the product stability of molecular structure, pattern is not significant changed during storage.

- **适用范围/Scope:** BG-T6066适用于各类锤纹漆。 BG-T6068适用于各类溶剂型镰纹涂料。

 - BG-T6066 applies to all types of hammer paint. BG-T6068 applies to all types of paint solvent hammer.

- **用量用法/Usage and dosage:** BG-T6066用量按配方总量的0.2%-2.0%,于调漆阶段加入。 BG-T6068用量按配方总量的0.3%-3.0%,于调漆阶段加入。
 - BG-T6066 formula by the total amount of 0.2%-2%, joining during painting stage. BG-T6068 formula by the total amount of 0.3%-3%, joining during painting stage.

本品只能喷涂不能刷漆,花纹大小粗细纹理设定,与添加量多少密切相关。

This product can only be used as spray not painting, pattern size and the thickness of the texture settings are directly bound up with added.