

型号		酸值	粘度	软化点	Tg	固化条件	特性说明
		(mgKOH/g)	P/200°C	°C	°C	°C/min	
1	XR7018	28-35	30-50	100-110	≥52	180/15	通用经济型70:30
2	XR7018C	30-38	25-40	105-115	≥56	180/15	高光泽、高流平，综合性能好
3	XR7018H	28-35	30-50	100-110	≥52	180/15	综合性能好,本品不含有机锡



Hybrid polyester resin for epoxy resin cure (70/30)

Type		Acid Value	Viscosity	Softening Point	Tg	Curing Condition	Properties
		(mgKOH/g)	P/200°C	°C	°C	°C/min	
1	XR7018	28-35	30-50	100-110	≥52	180/15	Economic polyester in common use.
2	XR7018C	30-38	25-40	105-115	≥56	180/15	High gloss, good flow leveling and good mechanical properties.
3	XR7018H	28-35	30-50	100-110	≥52	180/15	Excellent comprehensive properties with -out organotin.

混合型环氧固化聚酯树脂 70/30 系列

1	XR7018	28-35	30-50	100-110	≥52	180/15	通用经济型 70:30
2	XR7018C	30-38	25-40	105-115	≥56	180/15	高光泽、高流平，综合性能好
3	XR7018H	28-35	30-50	100-110	≥52	180/15	综合性能好,本品不含有机锡