

产品型号	PM-228	PM-1250	PM-668	PM-998
D97 $\mu\text{m}$	13.3	5.1	3.7	3.5
平均粒径 $\mu\text{m}$	4.7	2.5	1.4	1.2
最大粒径 $\mu\text{m}$	14	8	7	7
白度 %	86-94	86-94	88-94	88-94
比重 g/cm <sup>3</sup>	4.2-4.4	4.2-4.4	4.2-4.4	4.2-4.4
PH 值	7 $\pm$ 0.5	7 $\pm$ 0.5	7 $\pm$ 0.5	7 $\pm$ 0.5
水份%	$\leq$ 0.30%	$\leq$ 0.30%	$\leq$ 0.30%	$\leq$ 0.30%
吸油量 g/100g	13 ~ 15g/100g	13 ~ 15g/100g	13 ~ 15g/100g	13 ~ 15g/100g
900度烧失量%	1.2%	1.2%	1.1%	1.1%
325 目残余%	0.01%	0	0	0
铁含量%	$\leq$ 0.03%	$\leq$ 0.03%	$\leq$ 0.03%	$\leq$ 0.03%
钡含量%	$\geq$ 96%	$\geq$ 96%	$\geq$ 96%	$\geq$ 96%
净重	25	25	25	25