

# contents 目录

1\WATER BASE INK 水性油墨用颜料.....	01
2\SOLVENT BASE INK 溶剂体系油墨用颜料 .....	07
3\OFFSET BASE INK 胶印墨体系颜料 .....	11
4\MAINLY USED IN PAINT 涂料用颜料.....	15
5\MAINLY USED IN PLASTIC 塑料用颜料.....	23

# 水性油墨用颜料

## WATER BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic				
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints									
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint	塑料 Plastics		印花色浆 Textile Printing			
永固红HD-87 FAST RED HD-87	PR2	5	120℃	○				●	○								●	高光泽, 透明, 低粘度, 高冲淡色力, 黄相 High gloss, Transparent, Low viscosity, High tinting strength, Yellowish shade
永固红RC-266 FAST RED RC-266	PR4	7	120℃		○			●					●					高光泽, 高力份, 黄相 High gloss, High color strength, Yellowish shade
耐晒红RC-1022 FAST RED RC-1022	PR5	7	200℃					●	○	○	○			○			●	高光泽, 低粘度, 高冲淡色力 High gloss, Low viscosity, High tinting strength
永固红HD-68 FAST RED HD-68	PR8	5	120℃	○			○	●										高光泽, 低粘度, 高冲淡色力 High glossy, Low viscosity, High tinting strength
3132大红粉 3132 SCARLET RED	PR21	6	120℃		○		○	●	●									易分散, 低粘度 Easy dispersing, Low viscosity
颜料亮红RC-688 BRILLIANT FAST RED RC-688	PR22	5	140℃		○			●					○					高光泽, 易分散, 高冲淡色力, 蓝相 High gloss, Easy dispersing, High tinting strength, Bluish shade
坚固玫瑰红HD-3193 FAST CARMINE HD-3193	PR23	6	130℃	●				●	○									高光泽, 高力份 High gloss, High color strength
红青莲HD-BF BRILLIANT PURPLE HD-BF	PR31	5	150℃	●	○			●	○					○				高光泽, 高力份 High gloss, High color strength
耐晒大红HD-WI FAST SCARLET HD-WI	PR48:1	4	180℃					●									○	高光泽, 低粘度 High gloss, Low viscosity
耐晒大红RC-259 FAST SCARLET RC-259	PR48:2	5	180℃	○				●	○	○	○			○				高纯, 低粘度, 高光泽 High purity, Low viscosity, High gloss

# 水性油墨用颜料

## WATER BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing	
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint					
耐晒大红HD-W103 FAST SCARLET HD-W103	PR48:3	5	180℃		●			●								○	高光泽, 低粘度 High gloss,Low viscosity
立索尔大红RC-198 FAST SCARLET RED RC-198	PR49:1	4	130℃					●								○	高纯, 低粘度, 高光泽 High purity.Low viscosity,High gloss
立索尔深红HD-HW FAST DARK RED HD-HW	PR49:2	4	130℃		○			●								○	高光泽, 低粘度, 高冲淡色力 High gloss,Low viscosity,High tinting strength
色淀红RC-258 RED LAKE RC-258	PR53:1	4	140℃		○			●								○	高纯, 低粘度, 高光泽, 黄相 High purity,Low viscosity,High gloss,Yellowish shade
立索尔洋红RC-188 FAST RUBINE RC-188	PR57:1	5	170℃					●								○	高纯, 低粘度, 高光泽, 黄相 High purity,Low viscosity,High gloss,Yellowish shade
立索尔洋红RC-303 FAST RUBINE RC-303	PR57:1	5	170℃					●								○	高纯, 低粘度, 高光泽, 蓝相 High purity,Low viscosity,High gloss,bluish shade
永固桃红色原 FAST PINK TONE R	PR81	4	120℃					●									高光泽, 透明, 低粘度, 高冲淡色力 High gloss,Transparent,Low viscosity, High tinting strength
永固红HD-FGR FAST RED HD-FGR	PR112	6	150℃	○	○			●	○			○				○	高纯, 高光泽, 耐热, 耐候性好 High purity,Good heat resistance,High gloss, Good weather fastness
喹吡啶酮红RC-1170 QUINIDO RED RC-1170	PR122	7	250℃	○	○	○	○	●	○	○	●	○	○		●		高纯, 高光泽, 耐热性好 High purity,Good heat resistance,High gloss

# 水性油墨用颜料

## WATER BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
永固红HD-F3RK FAST RED HD-F3RK	PR170	7	200℃	○	○		○				●	●	○	○	●	高遮盖力, 流行性好, 耐热耐晒性好, 黄相, 适用于低铅汽车漆和工业漆 Good opacity and flow properties, Good heat resistance, Good lightfastness, Yellowish shade. Suitable for low-lead automotive and industrial paints
永固红F5RK FAST RED HD-F5RK	PR170	6	200℃	○	○		○				●	●	○	○	●	高纯, 耐热性好, 耐晒性好, 蓝相, 适用于各种工业漆 High purity, Good heat resistance, Good lightfastness. Bluish shade, Suitable for all type of industrial paints
永固宝红RC-152 FAST RUBINE RC-152	PR184	5	160℃	○					●	●	●				●	高纯, 低粘度, 高光泽 High purity, Low viscosity, High gloss
永固橙RC-3005 FAST ORANGE RC-3005	PO5	6	120℃						●	●	○				○	通用型 General application
永固桔黄HD-96 FAST ORANGE HD-96	PO13	3	150℃	●	●	○	○	●	●	○	○	○	●	●	●	通用型 General application
永固橙HD FAST ORANGE HD	PO16	7-8	170℃	●	●			○	●				●	○	●	通用型, 透明黄相 General application, Transparent, Yellowish shade
永固橙HD-139 FAST ORANGE HD-139	PO34	5	160℃	○	○	○		●						●	●	透明型, 高纯, 高光泽, 稳定性好 Transparent, High glossy, High purity, Storage stability
永固橙HD-HL FAST ORANGE HD-HL	PO36	7-8	240℃	●	●			●	○				●	●	●	通用型, 遮盖力和流动性好 General application, Very good opacity and flow properties
联苯胺黄RC-215 BENZIDINE YELLOW RC-215	PY12	3	180℃					●							○	高纯, 高光泽, 半透明红相 High gloss, High purity, Semi-Transparent, Reddish shade

# 水性油墨用颜料

## WATER BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
永固黄RC-1148 FAST YELLOW RC-1148	PY13	4-5	180 °C	●				●	○					●		高纯, 高光泽, 半透明黄相 High gloss, High purity, Semi-Transparent, Yellowish shade
永固黄RC-299 FAST YELLOW RC-299	PY14	3	180 °C					●							●	高纯, 高光泽, 蓝相 High gloss, High purity, Bluish shade
永固黄HD-117 FAST YELLOW HD-117	PY74	6	160 °C		●			●	○	○	○	●				高纯, 高光泽, 透明 High gloss, High purity Transparent
永固黄RC-277 FAST YELLOW RC-277	PY83	6	180 °C	○				○	●	○	○	●	●			高纯, 高光泽, 半透明绿相 High gloss, High purity, Semi-Transparent, Green
青莲色源RC-159 FAST BRONZE VIOLET RC-159	PV3	5	120 °C	○				●						○	○	高纯, 高光泽 High gloss, High purity
喹吡酮紫HD-3R QUINDO VIOLET HD-3R	PV19	7	250 °C	●	○	○	○	●	●							色相纯正红色, 耐晒性好 Clean reddish, Excellent light fastness
喹吡酮紫HD-201 QUINDO VIOLET HD-201	PV19	7	250 °C	●	●	○	●	●	○	○	●	○	○	○	○	蓝相, 高力份 Bluish, High strength grade
永固紫HD-256 FAST VIOLET HD-256	PV23	6-7	200 °C	○	○		○	●	○	○	○	○	○	○	●	高纯, 高光泽, 蓝相 High gloss, High purity, Bluish
永固紫HD-197 FAST VIOLET HD-197	PV23	6-7	200 °C	○				●						○	●	高纯, 高光泽, 红相 High gloss, High purity, Reddish
酞菁蓝BX (HD-403) PHTHALOCYANINE BLUE BX(HD-403)	PB15:0	7-8	200 °C	●				●	●				●	●	○	红光蓝相, 高力份, 色光鲜艳, 高光泽, 易分散 Reddish blue. High strength, Easy dispersing, Good hiding power

# 水性油墨用颜料

## WATER BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特 性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints						
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint	塑料 Plastics		印花色浆 Textile Printing
酞菁蓝B (HD-501A) PHTHALOCYANINE BLUE B(HD-501A)	PB15:0	7-8	200℃	●				●	●			●	●	●	绿光蓝相, 高力份, 色光鲜艳 Greenish blue,High strength,Brilliant shade
酞菁蓝B (HD-6840W) PHTHALOCYANINE BLUE B(HD-6840W)	PB15:0	7-8	200℃	●				●	●	○				●	高力份, 色光鲜艳, 高光泽, 易分散 High strength,Brilliant shade,Easy dispersing
酞菁蓝BS (HD-601) PHTHALOCYANINE BLUE BS(HD-601)	PB15:1	7-8	250℃	○		●		●	●		○	●	○	○	绿光蓝相, 不结晶, 耐溶剂, 耐热性好 Greenish blue,High strength,Non-crystallizing, Good resistance to solvent and heat
酞菁蓝BGS (HD-801) PHTHALOCYANINE BLUE BGS(HD-801)	PB15:3	7-8	250℃	●				●	●			●	●	●	红光蓝, 色光鲜艳, 高力份, 易分散 Reddish blue,Pure and brilliant shade,High color strength,Easy dispersing
酞菁蓝BGS (HD-810) PHTHALOCYANINE BLUE BGS(HD-810)	PB15:3	7-8	250℃	●				●	●			●	○	●	绿光蓝相, 高力份, 色光鲜艳, 高光泽, 易分散, 流动性好 Greenish blue,Easy dispersing,Brilliant shade , High flowability,Used for water base inks and paints
酞菁蓝BGS (HD-7084) PHTHALOCYANINE BLUE BGS(HD-7084)	PB15:3	8	220℃					●							在水相中易分散, 稳定性好 Good dispersed in water base,Good storage stability, Suitable for 42% water base ink
酞菁蓝RC-7101F PHTHALOCYANINE BLUE RC-7101F	PB15:4	8	240℃					●			○				不结晶, 不絮凝, 耐高温, 高力份 Non-crystallizing,Non-flocculating,High thermal stability, Brilliant shade,High color strength,Used in coloring at high temperature

# 水性油墨用颜料

## WATER BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing		
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水性墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint				乳胶漆 Emulsion Paint
酞菁绿 (HD-G) PHTHALOCYANINE GREEN(HD-G)	PG7	7-8	260℃	●	○	●	○	●	●		●	●	●	●	通用型, 黄相蓝相兼有 General application, Yellowish and bluish two shades.
酞菁绿 (HD-S) PHTHALOCYANINE GREEN(HD-S)	PG7	7-8	200℃	●	○	●		●	●		●	●	●	●	高力份, 色光鲜艳, 易分散 High strength, Good hiding power, Easy dispersing.

## 溶剂体系油墨用颜料 SOLVENT BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint					
耐晒大红HD-XL FAST SCARLET HD-XL	PR48:2	5	180℃	○	●	●	●	○									高光泽, 低粘度, 稳定性好, 透明, 适用于溶剂墨 High glossy, Low viscosity, High tinting strength, Storage stability, Transparent for solvent liquid inks
立索尔红HD-S6B FAST SCARLET RED HD-S6B	PR52:1	6	180℃		●		●			○	○	●	○	○			高光泽, 低粘度, 透明, 稳定性好 High glossy, Transparent, Low Viscosity, High tinting strength, Storage stability
色淀红RC-NF RED LAKE RC-NF	PR53:1	4	140℃	○	●	○	●	○							○		高光泽, 黄相 Bright transparent, Yellow shade, Outstanding rheological behaviour, High glossy
色淀红RC-PA RED LAKE RC-PA	PR53:1	3	140℃	○	●	○	○										高光泽, 透明, 低粘度, 稳定性好 High glossy, Transparent, Low viscosity, Storage stability
立索尔洋红HD-300 FAST RUBINE HD-300	PR57:1	5	170℃	○	○	●	●										流动性好 Excellent flow in solvent borne liquid inks
立索尔洋红HDB FAST RUBINE HDB	PR57:1	5	170℃		●	○	○										高光泽, 低粘度, 透明, 黄相, 稳定性好 High glossy, Transparent, Low viscosity, Yellowish shade, Storage stability
立索尔洋红HD-4BGL FAST RUBINE HD-4BGL	PR57:1	5	170℃		●	○											高光泽, 高透明, 强蓝灰色相, 适用于平版及凹版油墨 Excellent glossy, Transparent, Strong blueish shade for flexo and gravure inks
喹吡啶酮红RC-1171 QUINDO RED RC-1171	PR122	7	250℃	○	●	○	●	○	●	●	●	●	○	●			色光鲜艳, 耐热性好, 耐溶剂性好, 不迁移 Bright color, Strong coloring power, High heat resistance, Good solvent resistance and no migration property



## 溶剂体系油墨用颜料 SOLVENT BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing		
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	白干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint			乳胶漆 Emulsion Paint	
永固桃红HD-100 FAST PINK HD-100	PR146	5	160℃	●	●			●	○	○	○	○		●	高纯, 低粘度, 高光泽 High purity, Low viscosity, High gloss
永固桔黄HD-96 FAST ORANGE HD-96	PO13	3	150℃	●	●	○	○	●	●	○	○	○	●	●	通用型 General application
永固橙HD FAST ORANGE HD	PO16	7-8	170℃	●	●			○	●			●	○	●	通用型, 透明黄相 General application, Transparent, Yellowish shade
永固橙HD-GG FAST ORANGE HD-GG	PO34	5	160℃	●	●		○	○							高透明, 高光泽, 稳定性好 High transparent, High glossy, Storage stability
永固橙HD-HL FAST ORANGE HD-HL	PO36	7-8	240℃	●	●			●	○			●	●	●	通用型, 遮盖力和流动性好 General application, Very good opacity and flow properties
联苯胺黄HD-279 BENZIDINE YELLOW HD-279	PY12	5	180℃		●	●	●								高光泽, 透明, 低粘度, 稳定性好 High glossy, Transparent, Low Viscosity, Storage stability
永固黄HD-PA FAST YELLOW HD-PA	PY13	5	180℃		●										高光泽, 透明, 低粘度, 稳定性好 High glossy Transparent, Low Viscosity, Storage stability
永固黄HDBG FAST YELLOW HDBG	PY13	4-5	180℃	●	●	○	○	○							高光泽, 透明, 低粘度, 稳定性好 High glossy, Transparent, Low Viscosity, Storage stability
永固黄HD-GS FAST YELLOW HD-GS	PY14	3	180℃	○	●	○	○								高光泽, 透明, 低粘度, 稳定性好, 绿相 High glossy, Transparent, Low Viscosity, Storage stability, Greenish shade

## 溶剂体系油墨用颜料 SOLVENT BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing				
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint			乳胶漆 Emulsion Paint			
永固黄HD-5GF FAST YELLOW HD-5GF	PY14	3	180℃		○	●	●										高光泽, 半透明, 低粘度, 稳定性好, 绿相 High glossy, Semi-transparent, Low Viscosity, Storage stability, Greenish shade
永固黄HD-5GF-02 FAST YELLOW HD-5GF-02	PY14	3	180℃			●											高光泽, 高透明, 低粘度, 稳定性好, 绿相 High glossy, transparent, Low Viscosity, Storage stability, Greenish shade
颜料黄RC-4GT PIGMENT YELLOW RC-4GT	PY150	7-8	260℃	○	●					●	○	●	○				透明, 分散性好 Transparent and good dispersity
颜料黄155 (RC-4G) PIGMENT YELLOW 155 (RC-4G)	PY155	7-8	260℃	○	●	●	○										高透明, 高光泽, 低粘度 Transparent, High gloss, Low viscosity
青莲色源RC FAST BRONZE VIOLET RC	PV3	5	120℃		●				○								高光泽, 透明, 低粘度, 稳定性好 High glossy, Transparent, Low viscosity, Storage stability
永固紫RC-2000 FAST VIOLET RC-2000	PV23	7	200℃		●	●	●							●			高纯, 高光泽, 透明, 低粘度, 稳定性好 High purity, High glossy, Transparent, Low viscosity, Storage stability
酞菁蓝 (HD-03) PHTHALOCYANINE BLUE (HD-03)	PB15:2	7-8	260℃	●	●	●	●			●	●	●		○			红光蓝相, 色光鲜艳, 不结晶, 不结絮, 耐烘焙, 耐溶剂 Reddish blue, Brilliant shade, Non-crystallizing, Non-flocculating, Excellent resistance to baking and solvent

## 溶剂体系油墨用颜料 SOLVENT BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	白干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint				乳胶漆 Emulsion Paint	
酞菁蓝BGS (HD-808) PHTHALOCYANINE BLUE BGS(HD-808)	PB15:3	7-8	250℃	●	●	●	●			●	○					绿光蓝相, 易分散, 流动性好, 不结晶, 不结絮, 耐溶剂 More greenish blue, Easy dispersing, Excellent flowability, Good solvent resistance, Non-crystallizing, Non-flocculation
酞菁蓝RC-5412S PHTHALOCYANINE BLUE RC-5412S	PB15:4	8	230℃		●		○									低粘度, 不结晶, 不结絮 Non-crystallizing, Non-flocculating, Low viscosity
酞菁蓝HD-4000S PHTHALOCYANINE BLUE HD-4000S	PB15:4	8	200℃		●	●	○									低粘度, 不结晶, 不结絮, 适用于NC墨 Non-crystallizing, Non-flocculating, Low viscosity, Used in N/C inks
酞菁蓝HD-3000 PHTHALOCYANINE BLUE HD-3000	PB15:4	7	230℃		●	●	○									低粘度, 不结晶, 不结絮, 高光泽, 稳定性好 Non-crystallizing, Non-flocculating, Low viscosity, Good glossy and storage stability
酞菁绿 (HD-G) PHTHALOCYANINE GREEN(HD-G)	PG7	7-8	260℃	●	○	●	○	●	●		●	●	●	●		通用型, 黄相蓝相兼有 General application, Yellowish and bluish two shades.
酞菁绿 (HD-8730S) PHTHALOCYANINE GREEN(HD-8730S)	PG7	7-8	200℃	○	●			●	●		●	●		●		高力份, 色光鲜艳, 易分散 High strength, Good hiding power, Easy dispersing.

## 胶印墨体系颜料 OFFSET BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints							
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint	塑料 Plastics		印花色浆 Textile Printing	
立索尔大红HD-OF73 FAST SCARLET RED HD-OF73	PR49:1	4	130℃	●	○					○						高光泽, 高透明, 稳定性好 High glossy, High transparent, Storage stability
色淀红RC-OF08 RED LAKE RC-OF08	PR53:1	4	140℃	●										○		高光泽, 高透明, 稳定性好 High gloss, High transparent, Storage stability
立索尔洋红HDN FAST RUBINE HDN	PR57:1	5	170℃	●	○								○			高透明, 高光泽, 低粘度, 蓝相 Very transparent, High gloss, Low viscosity, Bluish shade
立索尔洋红HDD FAST RUBINE HDD	PR57:1	5	170℃	●												高透明, 易分散, 黄相 Very transparent, Easy dispersing, Yellowish shade
立索尔洋红HDE FAST RUBINE HDE	PR57:1	5	170℃	●												半透明, 高光泽, 低粘度, 中间色相 Semi-transparent, High gloss, Low viscosity, Middle shade
立索尔洋红HDH FAST RUBINE HDH	PR57:1	5	170℃	●	○	○										半透明, 高光泽, 低粘度, 蓝相 Semi-transparent, High gloss, Low viscosity, Bluish shade
立索尔洋红HDA FAST RUBINE HDA	PR57:1	5	170℃	●	○	○										高光泽, 高纯, 易分散, PH稳定性好, 黄相, 适用于平板印刷 High gloss, PH stability, High purity, Easy dispersing, Yellowish shade excellent litho properties
立索尔洋红HD-MB FAST RUBINE HD-MB	PR57:1	5	170℃	●	○	○										高光泽, 高纯, 易分散, PH稳定性好, 蓝相, 适用于平板印刷 High gloss, PH stability, High purity, Easy dispersing, Bluish shade excellent litho properties

## 胶印墨体系颜料 OFFSET BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	白干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
永固桔黄HD-96 FAST ORANGE HD-96	PO13	3	150℃	●	●	○	○	●	●	○	○	○	●	●	通用型 General application	
永固橙HD FAST ORANGE HD	PO16	7-8	170℃	●	●			○	●				●	○	●	通用型, 透明黄相 General application, Transparent, Yellowish shade
永固橙HD-GG FAST ORANGE HD-GG	PO34	5	160℃	●	●		○	○								高透明, 高光泽, 稳定性好 High transparent, High glossy, Storage stability
永固橙HD-HL FAST ORANGE HD-HL	PO36	7-8	240℃	●	●			●	○				●	●	●	通用型, 遮盖力和流动性好 General application, Very good opacity and flow properties
联苯胺黄HD-15 BENZIDINE YELLOW HD-15	PY12	3	180℃	●									○			半透明, 高流动性 Semi-Opaque, High-flow
联苯胺黄HDT BENZIDINE YELLOW HDT	PY12	3	180℃	●		○										高透明, 红相 High transparent, Reddish shade
永固黄RC-1148 FAST YELLOW RC-1148	PY13	4-5	180℃	●				●	○				●			高纯, 高光泽, 半透明黄相 High gloss, High purity, Semi-Transparent, Yellowish shade
永固黄G-16 FAST YELLOW HD-G16	PY14	3	180℃	●									●	○		高纯, 高光泽 High gloss, High purity
永固黄HDE FAST YELLOW HDE	PY174	6	180℃	●												高透明, 高光泽, 低粘度, 不易咬辊, 红相, 适合于胶印墨 Transparent, High gloss, Low viscosity, Good beadmill stability for offset inks, Reddish shade

## 胶印墨体系颜料 OFFSET BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint				乳胶漆 Emulsion Paint	
永固黄HDS FAST YELLOW HDS	PY174	4-5	180℃	●			○									高透明, 高光泽, 低粘度, 不易咬辊, 绿相, 适合于胶印墨 Transparent, High gloss, Low viscosity, Good beadmill stability for offset inks, Greenish shade
联苯胺黄HD-GRX BENZIDINE YELLOW HD-GRX	PY176	6	200℃	●	○						○		●	○		高透明, 高光泽, 易分散, 红相 Transparent, High gloss, Easy dispersing, Reddish shade
永固黄HDF FAST YELLOW HDF	PY188	4-5	180℃	●												高透明, 高光泽, 低粘度, 红相, 流动性好, 适合于胶印墨 Transparent, High gloss, Low viscosity, Reddish shade, Good flow for offset
酞菁蓝BX (HD-403) PHTHALOCYANINE BLUE BX (HD-403)	PB15:0	7-8	200℃	●				●	●				●	●	○	红光蓝相, 高力份, 色光鲜艳, 高光泽, 易分散 Reddish blue. High strength, Easy dispersing, Good hiding power
酞菁蓝B (HD-501A) PHTHALOCYANINE BLUE B (HD-501A)	PB15:0	7-8	200℃	●				●	●				●	●	●	绿光蓝相, 高力份, 色光鲜艳 Greenish blue, High strength, Brilliant shade
酞菁蓝BS (HD-602) PHTHALOCYANINE BLUE BS (HD-602)	PB15:1	7-8	260℃	●		●		○	○		○		○	○	○	红光蓝, 色相鲜艳, 不结晶, 耐溶剂, 耐热, 易分散 Reddish blue, Brilliant shade, Non-crystallizing, Good resistance to solvent, Heat and dispersancy

## 胶印墨体系颜料 OFFSET BASE INK

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints							
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint	塑料 Plastics		印花色浆 Textile Printing	
酞菁蓝BGS (HD-801) PHTHALOCYANINE BLUE BGS(HD-801)	PB15:3	7-8	250℃	●				●	●				●	●	●	红光蓝, 色光鲜艳, 高力份, 易分散 Reddish blue, Pure and brilliant shade, High color strength, Easy dispersing
酞菁蓝BGS (HD-807) PHTHALOCYANINE BLUE BGS(HD-807)	PB15:3	7-8	250℃	●				○	○					○	○	红光蓝, 色光鲜艳, 高力份, 易分散 Reddish blue, Pure and brilliant shade, High color strength, Easy dispersing
酞菁蓝BGS (RC-8700) PHTHALOCYANINE BLUE BGS(RC-8700)	PB15:3	7	220℃	●												高光泽, 流动性好, 适用于高速印刷用墨 High brightness, High flowability, Suitable for higher speed printing offset inks and heat-set inks
酞菁蓝BGS (RC-8700A) PHTHALOCYANINE BLUE BGS(RC-8700A)	PB15:3	8	220℃	●												高光泽, 易分散, 流动性好 High brightness, Easy dispersing, Good flowability
酞菁蓝BGS (RC-8500) PHTHALOCYANINE BLUE BGS(RC-8500)	PB15:3	8	230℃	●				○	○							流动性极好, 适用于热固型油墨及高速胶印用墨 Very excellent flowability and good ink function, Special used for thermoset inks and high-speed printing offset ink
酞菁蓝BGS (RC-7330) PHTHALOCYANINE BLUE BGS(RC-7330)	PB15:3	7	230℃	●												色相纯正, 高透明, 适用于高级胶印墨印刷 Pure and brilliant shade, High transparence, Used for high grade resin offset inks with gloss
酞菁绿 (HD-G) PHTHALOCYANINE GREEN(HD-G)	PG7	7-8	260℃	●	○	●	○	●	●		●	●	●	●	●	通用型, 黄相蓝相兼有 General application, Yellowish and bluish two shades.

## 涂料用颜料

MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint			乳胶漆 Emulsion Paint		
甲苯胺红HD-06 TOLUIDINE SCARLET RED HD-06	PR3	6-7	120℃							●	○					高光泽, 低粘度, 高冲淡色力 High gloss,Low viscosity,High tinting strength
3132大红粉 3132 SCARLET RED	PR21	6	120℃		○		○	●	●						●	易分散, 低粘度 Easy dispersing,Low viscosity
耐晒大红HD-2BM FAST SCARLET HD-2BM	PR48:4	6	180℃	○					○	●	●	○		○		耐热性好, 色光鲜艳 Good heat resistance,Bright color,Strong coloring power
立索尔红RC-302 FAST SCARLET RED RC-302	PR52:2	7	150℃						○	○	●	○				耐热性好, 色光鲜艳 Good heat resistance,Bright color,Strong coloring power
立索尔紫红HD-07 FAST MAROON HD-07	PR63:1	6	140℃	○						●				○		通用型 General application
永固红HD-FGR FAST RED HD-FGR	PR112	6	150℃	○	○				●	○			○		○	高纯, 高光泽, 耐热, 耐候性好 High purity,Good heat resistance,High gloss, Good weather fastness
喹吡啶酮红RC-1170 QUINIDO RED RC-1170	PR122	7	250℃	○	○	○	○	●	○	○	●	○	○		●	高纯, 高光泽, 耐热性好 High purity,Good heat resistance,High gloss
颜料红HD-630 PIGMENT RED HD-630	PR123	6-7	250℃							●	○	●	○	●		高光泽, 高力份, 耐晒性好 Good light fastness,High gloss,Strong coloring power
颜料红HD-358 PIGMENT RED HD-358	PR149	7	200℃							●	○	●	○	●		高光泽, 高力份, 耐晒性好 Good light fastness,High gloss,Strong coloring power



## 涂料用颜料 MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint			乳胶漆 Emulsion Paint		
永固红HD-F2RK FAST RED HD-F2RK	PR170	7	200℃	○	○					●	●	●		○	●	浅黄色相, 较HD-3RK遮盖性好, 耐光耐候性好 Slightly yellowish and more opaque than HD-F3RK with better light and weather fastness
永固红HD-F3RK FAST RED HD-F3RK	PR170	7	200℃	○	○		○				●	●	○	○	●	高遮盖力, 流行性好, 耐热耐晒性好, 黄相, 适用于低铅汽车漆和工业漆 Good opacity and flow properties, Good heat resistance, Good lightfastness, Yellowish shade. Suitable for low-lead automotive and industrial paints
永固红F5RK FAST RED HD-F5RK	PR170	6	200℃	○	○		○				●	●	○	○	●	高纯, 耐热性好, 耐晒性好, 蓝相, 适用于各种工业漆 High purity, Good heat resistance, Good lightfastness. Bluish shade, Suitable for all type of industrial paints
永固洋红HDM FAST CARMINE HDM	PR171	7-8	250℃	●	●			●	●					●	●	高纯, 易分散, 耐热耐晒性好 Easy dispersing, Good heat resistance, High purity, Good lightfastness
永固红HDT FAST RED HDT	PR175	7-8	250℃	●	●			●	●					●	●	高透明, 耐热耐晒性好 High transparent, Very high lightfastness and high heat resistance
永固洋红HD3C FAST CARMINE HD3C	PR176	7-8	250℃	○	○			○	●	○				●		蓝相透明红光 Bluish transparent red, Excellent fastness properties
坚固红HD-A3B FAST RED HD-A3B	PR177	8	250℃	●	○	○	○	○	○	○	○	●	○	●	○	高力份, 透明红光 High strength transparent red

## 涂料用颜料 MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特 性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints				塑料 Plastics		印花色浆 Textile Printing	
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
茈艳紫红HD-388 PIGMENT RED HD-388	PR179	7	250℃							●	○	●	○			透明栗色适用于汽车漆, 黄相 Transparent perylene maroon for metallic automotive finishes, yellowish shade
茈艳紫红HD-392 PIGMENT RED HD-392	PR179	7	250℃							●	○	●	○			透明栗色适用于汽车漆, 兰相 Transparent perylene maroon for metallic automotive finishes, Bluish shade
永固宝红RC-152 FAST RUBINE RC-152	PR184	5	160℃	○					●	●	●				●	高纯, 低粘度, 高光泽 High purity, Low viscosity, High gloss
永固洋红HD4C FAST CARMINE HD4C	PR185	7-8	250℃	●	●				●	●				●	●	蓝光红相 Bluish red with good fastness properties
DPP大红HD-B0 DPP PIGMENT RED HD-B0	PR254	8	250℃						●	●			●	●		色光鲜艳, 高力份, 耐热, 耐晒, 耐酸, 耐碱, 遮盖力高 Bright color, strong coloring power, high heat resistance, good light permanency and acid fastness and resistance to alkali and has no migration property. Opaque medium red excellent weather resistance
DPP大红HD-2030 DPP PIGMENT RED HD-2030	PR254	7-8	280℃							●				●		高透明, 高光泽, 易分散 Transparent, High gloss, Easy dispersing.
颜料红255(HD-5G) PIGMENT RED 255 (HD-5G)	PR255	7-8	260℃							●			●	●		高纯, 低粘度, 高光泽, 易分散 High purity, Low viscosity, High gloss, Easy dispersing.

## 涂料用颜料

### MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特 性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
永固橙RC-3005 FAST ORANGE RC-3005	PO5	6	120℃					●	●	○					○	通用型 General application
永固桔黄HD-96 FAST ORANGE HD-96	PO13	3	150℃	●	●	○	○	●	●	○	○	○	●	●	●	通用型 General application
永固橙HD FAST ORANGE HD	PO16	7-8	170℃	●	●			○	●			●	○	●	●	通用型, 透明黄相 General application, Transparent, Yellowish shade
永固橙HD-213 FAST ORANGE HD-213	PO34	5	160℃						●	●	●	○	○	○	○	良好的遮盖性和流动性 Excellent opacity and flow properties
永固橙HD-HL FAST ORANGE HD-HL	PO36	7-8	240℃	●	●			●	○			●	●	●	●	通用型, 遮盖力和流动性好 General application, Very good opacity and flow properties
耐晒橙HD-HFG FAST ORANGE HD-HFG	PO38	7-8	220℃			●			●	○	○	●	●	●	●	高纯, 低粘度, 高光泽, 易分散 High purity, Low viscosity, High gloss, Easy dispersing.
颜料橙64 (HD-GP) PIGMENT ORANGE 64 (HD-GP)	PO64	7-8	300℃						●	○	○	●	●			高纯, 低粘度, 高光泽, 易分散 High purity, Low viscosity, High gloss, Easy dispersing.
颜料橙71 (HD-TR) PIGMENT ORANGE 71 (HD-TR)	PO71	7-8	300℃						●			●	●			高纯, 低粘度, 高光泽, 易分散 High purity, Low viscosity, High gloss, Easy dispersing.
颜料橙73 (HD-RA) PIGMENT ORANGE 73 (HD-RA)	PO73	7-8	280℃		●			●	●			●	●			高纯, 低粘度, 高光泽, 易分散 High purity, Low viscosity, High gloss, Easy dispersing.

## 涂料用颜料 MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic			
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints								
				胺印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint	塑料 Plastics		印花色浆 Textile Printing		
汉沙黄RC-133 FAST YELLOW RC-133	PY1	6	160°C	○						●	○		●			○	高纯, 低粘度, 高光泽 High purity, Low viscosity, High gloss
汉沙黄RC-103 FAST YELLOW RC-103	PY3	6	150°C	○						●			●	○	○		高纯, 低粘度, 高光泽 High purity, Low viscosity, High gloss
红光黄HD-2RN BENZIDINE YELLOW HD-2RN	PY55	7	150°C							●				○	●		高纯, 高光泽 High gloss, High purity
永固黄HD-RN FAST YELLOW HD-RN	PY65	7	130°C					●	●					○	●		高纯, 高光泽 High gloss, High purity
永固黄HD-70 FAST YELLOW HD-70	PY74	6	160°C					○	○				●				高纯, 高光泽, 半透明 High gloss, High purity, Semi-transparent
永固黄HD-117 FAST YELLOW HD-117	PY74	6	160°C		●			●	○	○	○	●					高纯, 高光泽, 透明 High gloss, High purity, Transparent
永固黄HD-180 FAST YELLOW HD-180	PY74	6	160°C					●	●	●		●	○	●			高遮盖力, 中间黄相, 适用于无铅装饰漆 Opaque medium yellow shade, Suitable for lead-free and decorative paints
永固黄HD-02 FAST YELLOW HD-02	PY83	6	180°C	○					●	●	○		●				高纯, 高光泽, 透明 High gloss, High purity, Transparent
永固黄HD-206 FAST YELLOW HD-206	PY83	6	180°C	○	○		○	○	●	●	●	●	○	●			高遮盖力, 流动性好, 适用于工业漆 Excellent opacity and flow properties for industrial finishes

## 涂料用颜料 MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints					塑料 Plastics	印花色浆 Textile Printing	
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint			
永固黄HD-FGL FAST YELLOW HD-FGL	PY97	7	200℃	●	●			●	●	●	●		●	●	高遮盖力, 耐溶剂性, 耐晒性好, 适用于各种工业涂料 High hiding power, Good solvent resistance, Very lightfast yellow for paints and printing inks
颜料黄HD-3R PIGMENT YELLOW HD-3R	PY139	7-8	200℃	○	○			○	●	○	●	○		○	高遮盖力, 流动性好, 适用于无铅工业涂料 Opaque reddish yellow for lead-free industrial coatings
颜料黄RC-4GR PIGMENT YELLOW RC-4GR	PY150	7-8	260℃	○	●				●	○	●	○			红相 Reddish
颜料黄RC-4GG PIGMENT YELLOW RC-4GG	PY150	7-8	260℃	○	●				●	○	●	○			绿相 Greenish
永固黄HD4G FAST YELLOW HD4G	PY151	7-8	230℃	○	○		○			●	●		●		高遮盖力, 流动性好, 适用于汽车漆和工业漆 Excellent opacity and flow properties, Suitable for automotive, Industrial paints and plastic
永固黄HD-3G FAST YELLOW HD3G	PY154	7-8	250℃	●	●			●	●				●	●	耐候性好, 适用于汽车漆 Excellent durability for automotive paints and other high quality applications
颜料黄155 (HD-5GD) PIGMENT YELLOW 155 (HD-5GD)	PY155	7-8	260℃						●	●	○	●			高遮盖力, 流动性好, 适用于各种工业漆 Excellent opacity and flow properties, Suitable for Industrial paints
颜料黄HD-HG FAST YELLOW HD-HG	PY180	5	250℃	●	●								●	●	耐晒, 绿光黄相, 适用于粉末涂料 Good lightfastness, Greenish yellow shade, suitable for high temperature plastic applications, also powder and coll coatings

## 涂料用颜料

### MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
喹吡酮紫HD-101 QUINDO VIOLET HD-101	PV19	7	250℃	○	○	○	○	○	○	●	●	○	●	●	透明型, 蓝相, 高力份 Transparent, Bluish, High strength grade	
喹吡酮紫HD-3R QUINDO VIOLET HD-3R	PV19	7	250℃	●	○	○	○	●	●						色相纯正红色, 耐晒性好 Clean reddish, Excellent light fastness	
喹吡酮紫HD-5R QUINDO VIOLET HD-5R	PV19	7	250℃		●		●		●						透明, 高力份 Transparent, High strength grade	
喹吡酮紫HD-201 QUINDO VIOLET HD-201	PV19	7	250℃	●	●	○	●	●	○	○	●	○	○	○	蓝相, 高力份 Bluish, High strength grade	
永固紫HD-256 FAST VIOLET HD-256	PV23	6-7	200℃	○	○		○	●	○	○	○	○	○	●	高纯, 高光泽, 蓝相 High gloss, High purity, Bluish	
酞菁蓝BX (HD-403) PHTHALOCYANINE BLUE BX(HD-403)	PB15:0	7-8	200℃	●				●	●			●	●	○	红光蓝相, 高力份, 色光鲜艳, 高光泽, 易分散 Reddish blue. High strength, Easy dispersing, Good hiding power	
酞菁蓝BS (HD-601) PHTHALOCYANINE BLUE BS(HD-601)	PB15:1	7-8	250℃	○		●		●	●		○	●	○	○	绿光蓝相, 不结晶, 耐溶剂, 耐热性好 Greenish blue, High strength, Non-crystallizing, Good resistance to solvent and heat	
酞菁蓝 (HD-03) PHTHALOCYANINE BLUE (HD-03)	PB15:2	7-8	260℃	●	●	●	●		●	●	●		○		红光蓝相, 色光鲜艳, 不结晶, 不结絮, 耐烘焙, 耐溶剂 Reddish blue, Brilliant shade, Non-crystallizing, Non- floculating, Excellent resistance to baking and solvent	

## 涂料用颜料 MAINLY USED IN PAINT

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints				塑料 Plastics	印花色浆 Textile Printing	
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint			
酞菁蓝 (HD-6875) PHTHALOCYANINE BLUE (HD-6875)	PB15:2	7-8	260℃						●	●	●				用于工业涂料, 耐候性能优良, 易分散 Excellent resistance to weatherability, easy dispersed used for industry coatings.
酞菁蓝BGS (HD-801) PHTHALOCYANINE BLUE BGS(HD-801)	PB15:3	7-8	250℃	●				●	●			●	●	●	红光蓝, 色光鲜艳, 高力份, 易分散 Reddish blue, Pure and brilliant shade, High color strength, Easy dispersing
酞菁蓝BGS (HD-810) PHTHALOCYANINE BLUE BGS(HD-810)	PB15:3	7-8	250℃	●				●	●			●	○	●	绿光蓝相, 高力份, 色光鲜艳, 高光泽, 易分散, 流动性好 Greenish blue, Easy dispersing, Brilliant shade, High flowability, Used for water base inks and paints
酞菁绿 (HD-G) PHTHALOCYANINE GREEN(HD-G)	PG7	7-8	260℃	●	○	●	○	●	●		●	●	●	●	通用型, 黄相蓝相兼有 General application, Yellowish and bluish two shades.
酞菁绿 (HD-8730S) PHTHALOCYANINE GREEN(HD-8730S)	PG7	7-8	200℃	○	●			●	●		●	●		●	高力份, 色光鲜艳, 易分散 High strength, Good hiding power, Easy dispersing.
酞菁绿 (HD-S) PHTHALOCYANINE GREEN(HD-S)	PG7	7-8	200℃	●	○	●		●	●		●	●	●	●	高力份, 色光鲜艳, 易分散 High strength, Good hiding power, Easy dispersing.



## 塑料用颜料

### MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing				
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint			乳胶漆 Emulsion Paint			
耐晒大红HD-NP FAST SCARLET HD-NP	PR48:1	4	230℃												●		易分散, 耐热性好 Easy dispersing, Good heat resistance
耐晒大红HD-2BP FAST SCARLET HD-2BP	PR48:2	5	230℃												●		易分散, 耐热性好, 色光纯正 Easy dispersing, Good heat resistance, Good lightfastness, Bright blue shade, Excellent dispersibility in plastics
耐晒大红HD-2BSP FAST SCARLET HD-2BSP	PB48:3	5	230℃												●		黄相色光, 易分散, 耐热性好 Easy dispersing, Good heat resistance, Good lightfastness, Yellowish shade, Barium-free designed for plastics
色淀红RC-CP RED LAKE RC-CP	PR53:1	3	140℃	○											●		透明黄相, 易分散 Transparent yellow shade, Easy dispersing
立索尔洋红HD-4BP FAST RUBINE HD-4BP	PR57:1	5	170℃												●		易分散, 热稳定性好 Easy dispersing, Good heat resistance
喹吡啶酮红RC-1102 QUINDO RED RC-1102	PR122	7	250℃	●	○	○	○	○	○	○	○	○	○	○	●	○	粒径小, 分散性好特别适用于塑料体系 Fineness and Good dispersity for plastics
永固洋红HDM FAST CARMINE HDM	PR171	7-8	250℃	●	●			●	●						●	●	高纯, 易分散, 耐热耐晒性好 Easy dispersing, Good heat resistance, High purity, Good lightfastness
永固洋红HD3C FAST CARMINE HD3C	PR176	7-8	250℃	○	○			○	●	○					●		蓝相透明红光 Bluish transparent red, Excellent fastness properties



## 塑料用颜料 MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application											特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints					塑料 Plastics		印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	白干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
永固洋红HD4C FAST CARMINE HD4C	PR185	7-8	250℃	●	●			●	●				●	●	蓝光红相 Bluish red with good fastness properties	
永固红HD2B FAST RED HD2B	PR208	7-8	250℃	●	●			●	●				●	●	热电性好适用于PVC, 橡胶电缆等 Excellent dielectric properties, Applications in PVC, Rubber, cable sheathing	
DPP大红HD-2030 DPP PIGMENT RED HD-2030	PR254	7-8	280℃			○			●				●		高透明, 高光泽, 易分散 Transparent, High gloss, Easy dispersing.	
颜料红255 (HD-5G) PIGMENT RED 255 (HD-5G)	PR255	7-8	260℃						●				●	●	高纯, 低粘度, 高光泽, 易分散 High purity, Low viscosity, High gloss, Easy dispersing.	
永固桔黄HD-96 FAST ORANGE HD-96	PO13	3	150℃	●	●	○	○	●	●	○	○	○	●	●	通用型 General application	
永固橙HD FAST ORANGE HD	PO16	7-8	170℃	●	●			○	●				●	○	●	通用型, 透明黄相 General application, Transparent, Yellowish shade
永固橙HD-139 FAST ORANGE HD-139	PO34	5	160℃	○	○	○		●					●	●	透明型, 高纯, 高光泽, 稳定性好 Transparent, High glossy, High purity, Storage stability	
永固橙HD-HL FAST ORANGE HD-HL	PO36	7-8	240℃	●	●			●	○				●	●	●	通用型, 遮盖力和流动性好 General application, Very good opacity and flow properties

## 塑料用颜料 MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water-base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint				乳胶漆 Emulsion Paint	
耐晒橙HD-HFG FAST ORANGE HD-HFG	PO38	7-8	220℃			●				●	○	○	●	●	●	高纯, 低粘度, 高光泽, 易分散 High purity,Low viscosity,High gloss, Easy dispersing.
颜料橙64 (HD-GP) PIGMENT ORANGE 64 (HD-GP)	PO64	7-8	300℃							●	○	○	●	●		高纯, 低粘度, 高光泽, 易分散 High purity,Low viscosity,High gloss,Easy dispersing.
颜料橙71 (HD-TR) PIGMENT ORANGE 71 (HD-TR)	PO71	7-8	300℃							●			●	●		高纯, 低粘度, 高光泽, 易分散 High purity,Low viscosity,High gloss,Easy dispersing.
颜料橙73 (HD-RA) PIGMENT ORANGE 73 (HD-RA)	PO73	7-8	280℃		●			●	●				●	●		高纯, 低粘度, 高光泽, 易分散 High purity,Low viscosity,High gloss,Easy dispersing.
永固黄RC-1148 FAST YELLOW RC-1148	PY13	4-5	180℃	●				●	○					●		高纯, 高光泽, 半透明黄相 High gloss,High purity,Semi-Transparent, Yellowish shade
永固黄G-16 FAST YELLOW HD-G16	PY14	3	180℃	●										●	○	高纯, 高光泽 High gloss,High purity
永固黄2G FAST YELLOW 2G	PY17	6	180℃	○	●					●				●	●	高纯高光泽, 透明绿相 High gloss,High purity,Transparent,Greenish shade
永固黄HD-TRP FAST YELLOW HD-TRP	PY62	7	260℃											●		易分散, 耐热性好, 红相 Easy dispersing,Good heat resistance,Reddish shade

## 塑料用颜料 MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks				油漆 Paints				塑料 Plastics	印花色浆 Textile Printing			
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint				乳胶漆 Emulsion Paint	
永固黄HD-10G FAST YELLOW HD-10G	PY81	7	200℃	●	●			●	●					●	●	易分散, 耐热性好, 半透明, 绿相 Easy dispersing, Good heat resistance, Semi-transparent, Greenish grade
永固黄RC-277 FAST YELLOW RC-277	PY83	6	180℃	○				○	●	○	○		●	●		高纯, 高光泽, 半透明绿相 High gloss, High purity, Semi-Transparent, Green
颜料黄HD-2R PIGMENT YELLOW HD-2R	PY139	7	240℃											●		适用于EVA/RUBBER, PS and PC Suitable for EVA/Rubber, PS and PC
耐晒黄HD-AGR PIGMENT YELLOW HD-AGR	PY147	7-8	300℃	○	○						○			●	●	易分散, 耐热性好 Easy dispersing, Good heat resistance
颜料黄RC-4GP PIGMENT YELLOW RC-4GP	PY150	7-8	260℃											●		适用于塑料 Suitable for Plastics
永固黄HD4G FAST YELLOW HD4G	PY151	7-8	230℃	○	○		○				●	●		●		高遮盖力, 流动性好, 适用于汽车漆和工业漆 Excellent opacity and flow properties, Suitable for automotive, Industrial paints and plastic
颜料黄155 (HD-3GP) PIGMENT YELLOW 155 (HD-3GP)	PY155	7-8	280℃										●			适用于PVC, PP, PO, PS & PE Suitable for PVC, PP, PO, PS & PE
永固黄HD-WGP FAST YELLOW HD-WGP	PY168	7	260℃	○	○						○			●	○	绿相, 易分散, 耐热性好 Easy dispersing, Good heat resistance, Greenish shade

## 塑料用颜料 MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic	
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints						
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	白干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint	塑料 Plastics		印花色浆 Textile Printing
颜料黄HD-HGG FAST YELLOW HD-HGG	PY180	5	250℃	●	●			○				●	●	●	超透明, 适用于塑料 Strong Transparent grade for plastic applications
永固黄HD-RP FAST YELLOW HD-RP	PY183	8	300℃	○	○						○		●	○	红相, 易分散, 耐热性好 Easy dispersing, Good heat resistance, Reddish shade
永固黄HD-HGR FAST YELLOW HD-HGR	PY191	7	300℃	○	○						○		●	○	红相, 易分散, 耐热性好 Easy dispersing, Good heat resistance, Reddish shade
酞菁蓝BX (HD-404) PHTHALOCYANINE BLUE BX(HD-404)	PB15:0	7-8	200℃										●		红相, 高力份, 易分散, 色光鲜艳 More reddish blue, High color strength, Brilliant shade, Superfine, Easy dispersing, High gloss and widely used for high grade thermoplast coloring
酞菁蓝B (HD-502) PHTHALOCYANINE BLUE B (HD-502)	PB15:0	7-8	210℃	○						○			●		绿光蓝相, 高力份, 色光鲜艳, 高光泽, 易分散 Greenish blue, High strength, Easy dispersing, Good resistance to heat
酞菁蓝B (HD-6850P) PHTHALOCYANINE BLUE B(HD-6850P)	PB15:0	7-8	220℃										●		适用于EVA/RUBBER, PS and PC Suitable for EVA/RUBBER, PS and PC
酞菁蓝BS (RC-2721) PHTHALOCYANINE BLUE BS(RC-2721)	PB15:1	8	230℃										●		红相, 热稳定性好 Good resistance to heat, Brilliant, Reddish shade
酞菁蓝BS (KBSD) PHTHALOCYANINE BLUE BS(KBSD)	PB15:1	8	240℃									●	●		热稳压定性好, 适用于PP, PE, ABS 色母粒 Excellent resistance to heat and light fastness, Used for PP, PE, ABS

## 塑料用颜料 MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints						塑料 Plastics	印花色浆 Textile Printing
				胺印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水墨墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
酞菁蓝BS (HD-414) PHTHALOCYANINE BLUE BS(HD-414)	PB15:1	7	220℃				○	○						●	○	耐热性好 Good resistance to solvent and heat
酞菁蓝BGS (HD-801) PHTHALOCYANINE BLUE BGS(HD-801)	PB15:3	7-8	250℃	●				●	●				●	●	●	红光蓝, 色光鲜艳, 高力份, 易分散 Reddish blue, Pure and brilliant shade, High color strength, Easy dispersing
酞菁蓝BGS (HD-805) PHTHALOCYANINE BLUE BGS(HD-805)	PB15:3	7-8	250℃	○						●				●		红光蓝相, 高力份, 色光鲜艳, 热稳定性好, 易分散 Reddish blue, High color strength, Brilliant shade, Good resistance to heat, Easy dispersing, Used for various plastic coloring
酞菁蓝BGS (HD-806) PHTHALOCYANINE BLUE BGS(HD-806)	PB15:3	7-8	260℃	○										●		绿光蓝相, 易分散, 高力份, 耐热性好 Greenish blue, Easy dispersing, High color strength, Good resistance to heat, Used for various plastic coloring
酞菁蓝BGS (HD-B2G) PHTHALOCYANINE BLUE BGS(HD-B2G)	PB15:3	8	240℃			○								●		色光鲜艳, 高力份, 透明型适用于色母粒和塑料 Brilliant shade, High color strength, High thermal stability and transperance, Used in master batches of plastics
酞菁蓝BGS (RC-7090) PHTHALOCYANINE BLUE BGS(RC-7090)	PB15:3	8	240℃											●		耐高温, 易分散, 适用于PP. PE, ABS等色母粒 Resistance to high temperature and good dispersion, Suitable use for master batches of PP, PE, ABS etc

## 塑料用颜料 MAINLY USED IN PLASTIC

产品名称 Product Name	颜料索引号 Color index No.	牢度性能 Fastness Properties		应用领域 Recommended Application										特性 Characteristic		
		耐光性 Light Fastness	耐热性 Heat Fastness	油墨 Inks					油漆 Paints						塑料 Plastics	印花色浆 Textile Printing
				胶印墨 Offset Inks	溶剂墨 Solvent base Inks	甲苯墨 Toluene-base Inks	复合墨 Complex Inks	水基墨 Water base Inks	自干漆 Air Drying paint	硝基漆 Lacquers	烘漆 Stoving Paint	乳胶漆 Emulsion Paint				
酞菁绿(HD-G) PHTHALOCYANINE GREEN(HD-G)	PG7	7-8	260℃	●	○	●	○	●	●		●	●	●	●	通用型, 黄相蓝相兼有 General application, Yellowish and bluish two shades.	
酞菁绿(HD-8730WP) PHTHALOCYANINE GREEN(HD-8730WP)	PG7	7-8	300℃										●	适用于EVA/RUBBER, PBT, PA, PS and PC Suitable for EVA/RUBBER, PBT, PA, PS and PC		