

KQ-F05

水性超级防腐漆

WATERBORNE SUPER ANTISEPTIC PAINT

产品组成

PRODUCT COMPOSITION

该漆是由德国水性改性丙烯酸树脂、德国水性改性丙烯酸聚多元杂化树脂、印度环保有机颜料、去离子水、德国助剂、德国水性固化剂等双组份组成

The paint is made of German water-based modified acrylic resin, German water-based modified acrylic poly-hybrid resin, India's environmental organic pigments, deionized water, German additives, German water-based curing agent and other two components

性能用途

PROPERTIES AND APPLICATIONS

耐黄变、耐候性好，保光、保色性好平光、丰满度好，优异的附着力、高硬度、高耐磨性，超级的耐水性、耐油、耐溶剂及化学品性，超级耐湿热、耐盐雾性好。用于机械设备、搅拌罐、桥梁、贮罐、集装箱、配电房，沿海各种设施等。

技术指标

TECHNICAL SPECIFICATIONS

颜色:各色 Color: Any color

光泽度%:0-70 Lustrousness, %:0-70° /按客户要求 or customized by the customer

细度 um:s 20um Degree of fineness, um:≤20um

附着力级(划格法):0- 1 级 Adhesion level (cross cut method ): 0-1 level

漆膜外观:光滑平整 Appearance of paint film: Flat and smooth

遮盖力,g/mi:120- 150g/m' Hiding power/g/ mt: 120- 150g/mf

耐冲击:2≥50kg.cm Impact resistance: z50kg. cm

硬度:≥2H Hardness:≥2H /容器中状态:均匀 Condition in container: uniform

耐水性:500h 不起泡，不剥落不生锈，不开裂

Water resistance: No blistering, no flaking, no rust, no cracking within 500h

耐盐雾:1000h 不起泡，不剥落，不生锈，不开裂

Salt spray resistance: No blistering, no flaking, no rust, no cracking within 1000h

耐人工气候老化:800h 不起泡，不开裂不脱落，不粉化≤1,失光 s2 级，变色≤2 级

Artificial weathering aging No blistering, no cracking, no flaking nonchalking≤1,

Dulling: s2 level, Discoloring:s2 level within 800h

固含量:≥50 Solid content:250 /流出时间 S(4 号杯):260S Time of outflow S(No 4 Cup): 60S

弯曲试验,mm:s 1mm Bending test,mm:s 1mm

干燥时间(小时): Drying time(h)

表干(25° C,h):2h Surface dry(25° C, h): 2h

实干(25°c,h):24h Full drying(25° C h):24h