

固体丙烯酸树脂 A-66

SOLID ACRYLIC RESIN A-66

典型性质: (Properties)

外观 (Appearance)	白色珠状 (White beads)
固体含量 (%) (Solid Content)	>99
软化点 (°C) (Softening Point)	130 - 150
酸值 mgKOH/g (Acid Value)	3 - 6
玻璃化温度 Tg (°C)	50
分子量 Mw	48000
粘度 mpa.s (25°C) (Viscosity)	1800 - 4500
(51%乙酸乙酯中) (51% in ethyl acetate)	

溶解性: (Solubility)

A-66 树脂溶于酯类、酮类、芳烃类溶剂，不溶于醇类和 200#溶剂。

It is soluble in ester, ketone and aromatics. It is insoluble in 200# gasoline and alcohol.

特性: (Characters)

- 1、良好的光泽度及硬度 (Good gloss and hardness)
- 2、与 CAB 相容性好 (Good compatibility with CAB)
- 3、良好的耐候性、耐化学品性 (Good resistance to weather or chemicals)
- 4、不回粘、良好的流平性 (Good leveling and no after tack)
- 5、对颜料分散性好 (Good pigment dispersion)

应用: (Application)

- 1、塑料涂料 (Plastic paint)
- 2、集装箱涂料 (Container paint)
- 3、油墨 (Inks)
- 4、罩光清漆 (Varnish)

包装: (Package)

25KG/袋 (25KG/bag)

贮存: (Storage)

本产品常温下贮存在干燥、通风处，避免潮湿，有效贮存期为 2 年。

Store in the place where is dry and installed with ventilation equipment, not in wet place. Its shelf life is 2 years.

以上资料仅供参考，本公司不作法律担保及不负任何法律责任。建议客户选用树脂之前应按自己要求进行应用方面的测试，以检验是否适用。