

微细球形铝粉 Fine Spherical Aluminum Powder

粒度均匀，分布区窄

Powder particle size well-distributed and narrow span.

杂质含量少，铝含量99.75%以上


Low impurities content, aluminum content 99.75% minimum.

外观呈银灰色，无外来夹杂物和结团，水分含量低，可长期储存

Silver-gray appearance, no foreign matter or powder agglomeration, low moisture content, allowing long time storage.

球形度好，振实密度高

Good sphericity, high tap-density.



规格名称 Specification	平均粒度 D50(um) 筛网分析 Sieve Analysis	化学成份 Chemical Composition				
		铝 Al (≥ %)	杂质含量 Impurity Content (≤ %)			
			铜 (Cu)	铁 (Fe)	硅 (Si)	水份 (H ₂ O)
FLPN1.5	1.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN2.5	2.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN3.5	3.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN4.5	4.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN5.5	5.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN6.5	6.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN7.5	7.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN8.5	8.5±0.5	99.75	0.015	0.20	0.20	0.10
FLPN10	10±1	99.75	0.015	0.20	0.20	0.10
FLPN12	12±1	99.75	0.015	0.20	0.20	0.10
FLPN14	14±1	99.75	0.015	0.20	0.20	0.10
FLPN16	16±1	99.75	0.015	0.20	0.20	0.10
FLPN18	18±1	99.75	0.015	0.20	0.20	0.10
FLPN20	20±1	99.75	0.015	0.20	0.20	0.10
FLPN22	22±1	99.75	0.015	0.20	0.20	0.10
FLPN25	25±1	99.75	0.015	0.20	0.20	0.10
-80目	+40 mesh: < 5%	99.75	0.015	0.20	0.20	0.10
	-80 mesh: ≤20%					
-30目	+60 mesh: < 8%	99.75	0.015	0.20	0.20	0.10
	-200 mesh: ≤35%					
-20目	+60 mesh: 0	99.75	0.015	0.20	0.20	0.10
	-150 mesh: ≤35%					
-10目	+150 mesh: < 5%	99.75	0.015	0.20	0.20	0.10
	-325 mesh: ≤50%					
-5目	+200 mesh: 4-9%	99.75	0.015	0.20	0.20	0.10
	-325 mesh: 75-85%					
-2目	+325 mesh: ≤15%	99.75	0.015	0.20	0.20	0.10