
































水性涂料色浆

迪纳尔水性涂料色浆，由高品质颜料及助剂制作而成，其质地均匀，色泽饱满，品质稳定，与各类水性体系相容性良好，具有较高的耐候性和较强的着色力，环保性好，VOC 含量低，广泛应用于内外墙乳胶漆、水性丙烯酸磁漆、水性聚氨酯漆、水性环氧漆、水性聚酯漆等。

产品代码	产品名称	颜色	颜料索引号	颜料份 (%)	耐光性 (级)		耐候性 (级)		耐碱性 (级)	耐酸性 (级)	耐热性 (℃)
					TT	ST	TT	ST			
8880728	耐晒黄		P. Y. 109	40	7-8	7	4-5	4	5	5	200
8880517	鲜黄		P. Y. 154	35	8	7-8	5	4-5	5	5	180
8880242	金黄		P. Y. 83	35	7-8	7	4-5	4	4-5	4-5	200
8880244	深黄		P. Y. 110	35	8	7-8	5	4-5	5	5	220
8880462	桔红		P. O. 42	42	7-8	7	4-5	4	4-5	4-5	160
8880460	桔橙		P. O. 73	34	8	7-8	5	4-5	5	5	160
8880209	氧化铁黄		P. Y. 42	65	8	8	5	5	5	5	180
8880315	氧化铁红		P. R. 101	70	8	8	5	5	5	5	180
8880326	氧化铁红		P. R. 101	70	8	8	5	5	5	5	180
8880306	氧化铁红		P. R. 101	70	8	8	5	5	5	5	180
8880486	耐晒红		P. R. 254	35	7-8	7	4-5	4	5	5	180
8880198	鲜红		P. R. 254	42	7-8	7	4-5	4	5	5	180
8880199	艳红		P. R. 254	35	8	7-8	5	4-5	5	5	180
8880422	品红		P. R. 122	35	7-8	7	4-5	4	5	5	180
8880411	紫红		P. R. 19	30	7-8	7	4-5	4	4-5	4-5	200
8880919	青莲紫		P. V. 23	32	7-8	7	4-5	4	4-5	4-5	180
8880561	配蓝		P. B. 15: 1	48	8	8	5	5	5	5	180
8880562	配蓝		P. B. 15: 3	52	8	8	5	5	5	5	180
8880911	配绿		P. G. 7	48	8	8	5	5	5	5	200
8880718	碳黑		P. BK. 7	35	8	8	5	5	5	5	200
9990740	亮黄		P. Y. 74	48	6-7	6	4	3-4	4-5	4-5	160
9990112	亮红		P. R. 112	48	6-7	6	4	3-4	4-5	4-5	160
9990488	大红		P. R. 170	36	6-7	6	4	3-4	4-5	4-5	180
9990561	配蓝		P. B. 15: 1	35	8	8	5	5	5	5	180
9990562	配蓝		P. B. 15: 3	35	8	8	5	5	5	5	180
9990518	碳黑		P. BK. 7	30	8	8	5	5	5	5	200
9990111	氧化铁黄		P. Y. 42	55	8	8	5	5	5	5	180
9990222	氧化铁红		P. R. 101	70	8	8	5	5	5	5	180
9990333	氧化铁红		P. R. 101	70	8	8	5	5	5	5	180
9990190	深铁红		P. R. 101	70	8	8	5	5	5	5	180
9990666	氧化铁橙		P. R. 101P. Y. 42	60	8	8	5	5	5	5	180
9990618	氧化铁黑		P. BK. 11	60	8	8	5	5	5	5	200