

# CDS Nature stone coating

## 厦光CDS天然真石漆



### 产品简介：

以纯丙烯酸乳液为粘结剂，采用天然花岗岩碎粒为主要展色系统研制而成，外观庄重严肃，充分展现天然石的丰富质感，具有优异的耐候性、防水性、保色性，是一种既豪华又经济的天然真石漆。

### Product features:

Based on pure acrylic emulsion Binder, the use of natural granite pieces as the main vehicle system developed by, the appearance of serious, full of the rich texture of natural stone, with excellent weather resistance, water resistance and color retention, is a natural really stone paint both luxury and economy.

### 性能特点：

- 天然石材质感
- 优异的耐候性
- 弥盖墙体裂缝
- 耐黄变
- 附着力强
- 造价经济
- 永不褪色
- 防水性好
- 与保温匹配性好

### Features:

- Natural stone texture
- Excellent weatherability
- Masked wall cracks
- Non-yellowing
- Strong adhesion
- Economic price
- Never fade
- Good waterproofing
- And holding a good matching



### 适用场所：

各种建筑物内外墙装饰，完全可以装饰出天然石的效果，尤其适合于外墙外保温工程等。

### Application of places:

A variety of Interior and exterior wall decoration, completely decorative natural stone effect, particularly suitable for exterior wall thermal insulation works.

### 技术参数：

基 料：纯丙烯酸聚合物乳液。  
 颜 色：样板、色卡或提供来样。  
 产 品 特 征：水溶性、彩色、厚质。  
 干 燥 时 间：表干12小时，重涂24小时，实干48小时（温度25℃，相对湿度80%）。  
 理论耗漆量：4.5-5.5kg/m<sup>2</sup>，实际涂布量因基面粗糙程度、施工方法、花型不同而略有差异。

### Technical parameters:

Base material: Pure acrylic polymer emulsion.  
 Color: Templates, color cards or provide sample.  
 Product features: Water soluble, coloured, thick texture.  
 Drying time: Surface dry for 12 hours, re-coating 24 hours, work 48 hours (temperature 25℃, relative humidity 80%)  
 The consumption of paint: 4.5-5.5kg/m<sup>2</sup>. The actual coating caused by surface roughness, slightly different construction methods, designs vary.


### 施 工：

施工方法：专用喷枪喷涂。  
 稀释比例：不宜加水稀释，以免影响装饰效果。确有需要可酌加5%以内清水稀释。  
 施工要求：在5℃ - 35℃及相对湿度80%以下施工。大风、下雨等恶劣天气应避免施工。

### Technical parameters:

Construction method: special spray.  
 Dilution ratio: should not be diluted with water, so as not to affect the decorative effect. Genuine need may be subject to additional 5% less than clear water dilution.  
 Construction requirements: 5℃-35℃, relative humidity below 80% construction. Construction of wind, rain and other inclement weather should be avoided.

### 施工工艺 Construction technology



- ① 基 层：厦光中层柔性腻子/厦光专用中层腻子2-3遍
- ② 底 层：厦光抗碱封闭底漆1遍
- ③ 中 层 一：厦光CDS天然真石漆1遍
- ④ 中 层 二：厦光CDS天然真石漆1遍
- ⑤ 面 层：厦光罩面涂料1-2遍

- ① The grass-roots level: Dedicated middle managers Middle flexible PUTTY/Terminal light PUTTY 2-3
- ② Bottom: Alkali-resistant primer 1 times
- ③ Middle layer: Natural really stone paint CDS 1 times
- ④ Intermediate II: Natural really stone paint CDS 1 times
- ⑤ Surface: Overlay coating 1-2

### ■ 天然彩色石砂性能指标

Natural colored stone sands performance indicators

主要特性 Key Features
色彩稳定 Color stability
耐酸碱 Acid resistance
抗曝晒 Anti-exposure
永不褪色 Never fade
颗粒匀称 Particle symmetry
硬度适中 Moderate hardness