

产品	深色	浅色	颜色索引号	比重	颜料含量	耐光性		耐候性		耐化学性		渗色	耐热
Products	1/3 ISD	1/25 ISD	C.I.NO	Density	Pig%	1/3	1/25	1/3	1/25	酸	碱	Bleeding	Heat
明黄2041			PY14	1.02	23	6	3-4	2-3	1-2	5	5	2	150
铁黄2042			PY42	1.91	68	8	8	5	5	5	5	5	200
菊黄2082			PY83	1.05	40	7	6-7	4	3	5	5	4	180
透明深黄2083			PY83	1.01	18	7	6-7	4	3	5	5	4	180
鲜黄2097			PY97	1.09	30	8	7-8	5	4-5	5	5	5	200
金黄2110			PY110	1.02	18	8	8	5	5	5	5	5	200
喹啉黄2138			PY138	1.05	40	7	6	4	3-4	5	4-5	5	200
青金黄2154			PY154	1.02	24	8	8	5	5	5	5	5	200
鲜橙3073			PO73	1.02	24	8	7-8	5	4-5	5	5	5	200
铁红4102			PR101	1.62	65	8	8	5	4-5	5	5	5	200
玫红4122			PR122	1.01	20	8	7-8	5	4-5	5	5	5	200
鲜红4170			PR170	1.03	24	7	6	4	3	5	5	3	180
宝红4171			PR171	1.02	24	7	6-7	4	3	5	5	4	180
透明红4177			PR177	1.01	12	7-8	7	4-5	4	5	5	5	200
正红4254			PR254	1.05	23	8	7-8	5	4-5	5	5	5	200
永固紫5023			V23	0.96	12	7-8	7	4-5	4	5	5	5	200
群青蓝6028			PB29	1.43	50	8	8	4-5	4-5	3	3	5	200
青蓝6153			PB15:3	1.02	21	8	8	5	5	5	5	5	200