

封闭型异氰酸酯

品名 Product Name	溶剂 Solvent	粘度 Visc	固体份% NV	异氰酸酯 Isocyanate	特性及用途 Properties Application
SY9075	S-100	Y-Z2	75	HDI	脂肪族，用于工业面漆，卷材涂料和抗石击底漆耐候和不黄变烘烤涂料；也可作为添加剂改善附着力和柔韧性。 Aliphatics, non-yellowing baking systems for industrial finishing, coil and tone-chip primer surfacers; also as an additive to improve adhesion and flexibility
SY9170	混合溶剂 Mixed solvent	U-Y	70	脂肪型 Aliphatics	脂肪族，低温解封和高温不黄变的卷材涂料和抗石击底漆耐候烘烤涂料；也可作为添加剂改善附着力和柔韧性 Aliphatics, low temperature deblocking non-yellowing baking systems for industrial finishing, coil and tone-chip primer surfacers; also as an additive to improve adhesion and flexibility
SY9180	混合溶剂 Mixed solvent	3500-8500	80	TDI	适用于工业烤漆 Suitable for industrial baking enamel