

消光粉

型号 Type:	SiO <sub>2</sub> 含量 ( 干基 ) , % SiO <sub>2</sub> Content	孔隙率, (M/g) Porosity:	吸油值 ( g/100g) Oil absorption value	平均粒径 d50 ( μm ) Particle size	干燥失重, ≤ % ( 105℃, 2Hrs ) , % Drying Loss	灼烧失重, ≤ % ( 1000℃, 2Hrs ) , % Ignition loss	白度, ≥ Whiteness	PH 值, (5% 悬浮液 ) PH value (5% Aqueous suspension)	表面处理 Surface treatment
HF-610	≥ 99	1.8	260~320	5.0	≤ 5	≤ 5	≥ 94	5~8	特殊处理 Special treatment
HF-610L	≥ 99	1.8	260~320	5.0	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-620	≥ 99	1.8	260~320	5.5	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-620L	≥ 99	1.8	260~320	5.5	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-630	≥ 99	1.8	260~320	5.8	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-630L	≥ 99	1.8	260~320	5.8	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-650	≥ 99	1.8	260~320	6.3	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-650L	≥ 99	1.8	260~320	6.3	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-660	≥ 99	1.8	260~320	7.0	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-660L	≥ 99	1.8	260~320	7.0	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-900	≥ 99	1.8	260~320	6.0	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-900L	≥ 99	1.8	260~320	6.0	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-950	≥ 99	1.8	260~320	6.2	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-950L	≥ 99	1.8	260~320	6.2	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-955	≥ 99	1.8	260~320	6.5	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-955L	≥ 99	1.8	260~320	6.5	≤ 5	≤ 15	≥ 94	5~8	有机 Organic
HF-975	≥ 99	1.8	260~320	7.5	≤ 5	≤ 5	≥ 94	5~8	特殊 Special treatment
HF-860	≥ 99	1.2	160~190	6.0	≤ 5	≤ 5	≥ 94	5~8	无 NO
HF-865	≥ 99	1.2	160~190	6.5	≤ 5	≤ 5	≥ 94	5~8	无 NO
HF-870	≥ 99	1.2	160~190	7.0	≤ 5	≤ 5	≥ 94	5~8	无 NO
HF-875	≥ 99	1.2	160~190	7.5	≤ 5	≤ 5	≥ 94	5~8	无 NO