

颜料黄系列

色卡		参考 编号 及 产品 名称	索引号	物化数据			牢度性能					应用推荐						
本色	冲淡 色			PH 值	比 重	吸 油 量	耐 光	耐 热	耐 水	耐 油	耐 酸	耐 碱	水 基 墨	溶 剂 墨	胶 印 墨	塑 胶	油 漆	花 色 浆
		815 1 有 机嫩 黄		6.5-7. 5	1. 5	35	7	16 0	5	5	4	4	●	◎	◎	●		
		812 5 耐 晒黄 G	C.I.PY1	6.5-7. 5	1. 5	40	7	16 0	5	4	5	5	●	◎	◎	◎	●	◎
		810 4 耐 晒黄 10G	C.I.PY3	6.5-7. 5	1. 5	50	7	16 0	5	5	5	5	●	◎	◎	◎	●	◎
		810 3 联 苯胺 黄 G	C.I.PY1 2	6-7	1. 5	45	5	18 0	4	4	5	5	◎	●	◎	◎	◎	●
		811 5 联 苯胺 黄 G	C.I.PY1 2	6-7	1. 5	45	5	18 0	4	4	5	5		●				
		682 1 联 苯胺 黄 G	C.I.PY1 2	6-7	1. 5	45	5	18 0	4	4	5	5		●	◎			
		682 2 联 苯胺 黄 G	C.I.PY1 2	6-7	1. 5	45	5	18 0	4	4	5	5		●	◎			
		812 2 永	C.I.PY1 3	6-7	1. 6	45	5	18 0	4	4	5	5	●	◎	◎	◎	●	

	固黄 10G																	
	811 0 永 固黄 HR	C.I.PY8 3	6.5-7	1. 6	35-4 5	7- 8	25 0	5	5	5	5	●	◎	◎	◎	●	◎	
	811 1 永 固黄 HR- B	C.I.PY8 3	6.5-7	1. 6	35-4 5	7- 8	25 0	5	5	5	5	●				●	●	
	688 1 永 固黄 HR	C.I.PY8 3	6.5-7	1. 6	35-4 5	7- 8	25 0	5	5	5	5	◎	◎	◎	●	●	◎	●
	688 2 永 固黄 HR	C.I.PY8 3	6.5-7	1. 6	35-4 5	7- 8	25 0	5	5	5	5				●			
	688 3 永 固黄 HR	C.I.PY8 3	6.5-7	1. 6	35-4 5	7- 8	25 0	5	5	5	5	●	◎	◎		●	●	
	688 5 永 固黄 HR	C.I.PY8 3	6.5-7	1. 6	35-4 5	7- 8	25 0	5	5	5	5			◎	●		●	

● 推荐用途 ◎ 选择使用

注：以上仅作参考，确切数据以技术部提供报告为准。